

10-8 EPDM Sponge

Description:

EPDM with a high bonding adhesive to the sponge material is used to fill gaps between exterior moldings and enameled metals in order to seal against air and noise intrusion. The high adhesion provides suitability to a variety of materials, and is a convenient application for automotive interior. In areas where low force to compress is required.

Typical Properties:

Density:	4 to 7 lbs./ft ³
Thickness:	3mm (min)
Adhesive:	Acrylic
Compression Load Deflection (25%):	2 kPa
Tensile Strength:	250 kPa
Elongation:	200%
Flammability:	Pass

Temperature Range:

Intermittent Max.:	-280°F
Continuous Max.:	-250°F
Low Min.:	-60°F

OEM Standards:

Testing may be required

GMW: 15473 Class 1 Type 1

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.